



**ZINC US-MIL-A-18001k ALLOY SPECIFICATION**

Components:

Al 0,1-0,5% range  
 Fe 0,005% max  
 Pb 0,006% max  
 Cd 0,025-0,07% Max  
 Cu 0,005% max  
 Zn remaining

Capacity: 780 Ah/kg

Efficiency: 95%

Potential: - 1110 mV Cu -

CuSO<sub>4</sub> electrolyte artificial sea water DIN 50905

Insert quality: Plate, bar section EN10025 Grade S235/S275

Insert welding: All fabrication of steel inserts are according EN10287 and EN10288

NET WEIGHT: 0,9 kg  
 GROSS WEIGHT: 1,0 kg  
 INSERT WEIGHT: 0,1 kg

Company address:  
 Tinstraat 109  
 2984AN Ridderkerk  
 The Netherlands  
 Tel. +31 (0) 180 420 055  
 Fax. +31 (0) 180 499 810  
 E-mail. info@nedmarine.com  
 www.nedmarine.com



Drawing name: <b>NED 9Z</b>			
Drawing No.: 17.0189	Rev: 0	Sheet: 1/1	
Drawn: A.M.	Approved: G.M.	Scale: -	Date: 04/11/2016

Ned T.D. 16 003